



Various Gases Barrier Property of "SoarnoL™"

Various gases barrier property of "SoarnoL[™]" is shown in the following. Permeability for various gases is expressed by the following formula.

P=D·S

Here P:Permeability coefficient, D:Diffusion coefficient, S:Solubility coefficient By comparison of N2, O2 and CO2, the difference of each gas permeability is due to the difference of solubility between gas molecule and "SoarnoLTM" for each gas.

On the other hand, by comparison of He and other gases, the difference of gas permeability is due to the difference of diffusion between He molecule and other gas molucule for "SoarnoL[™]".

Sample	Gas Permeability (cc 20µm/m² day atm)			
	N2	O2	CO ₂	He
Soarnol 29mol%	0.018	0.23	0.49	110
Soarnol 32mol%	0.024	0.3	0.62	120
Soarnol 38mol%	0.041	0.53	1.3	180
Soarnol 44mol%	0.1	1.2	4.4	320
ONy	11	24	180	1,700
PET	7.8	30	96	2,600
OPP	600	1,400	10,500	25,000

Condition : 20deg C, Dry atmosphere Dry film, with Differential Pressure Method

MITSUBISHI CHEMICAL CORPORATION

Advanced Polymers Business Domain, Performance Polymers Div. Soarnol Dept. 1-1, Marunouchi 1-Chome, Chiyoda-Ku, Tokyo 100-8251, Japan TEL +81-3-6748-7803 FAX +81-3-3286-1239

• Due to printing characteristics, the color tones may differ from the actual ones.

• The transcription of any data or information contained in this sheet without

prior written consent is strictly prohibited.

[•] The content of this sheet may be changed without prior notice.