



Relationship between Relative Humidity and Tg

Glass transition temperature (Tg) for each relative humidity with "Soarno⊔™" is shown in the following.

(1) Evaluation Method
Sample : SoarnoL (32mol%, 38mol%, 44mol%)
Apparatus : Perkin Elmer DSC7
Programming rate : 10deg.C/min

(2) Result

Sample	Tg (deg. C)					
	0%	45%	65%	72%	88%	100%
SoarnoL 32mol%	60	38	37	16	-	3
SoarnoL 38mol%	58	40	37	38	18	6
SoarnoL 44mol%	55	38	36	37	-	8

MITSUBISHI CHEMICAL CORPORATION

Advanced Polymers Business Domain, Performance Polymers Div. Soarnol Dept. 1-1, Marunouchi 1-Chome, Chiyoda-Ku, Tokyo 100-8251, Japan TEL +81-3-6748-7803 FAX +81-3-3286-1239

• Due to printing characteristics, the color tones may differ from the actual ones.

• The transcription of any data or information contained in this sheet without

prior written consent is strictly prohibited.

[•] The content of this sheet may be changed without prior notice.