

# **Soarnol™ BG3522B**

ETHYLENE VINYL ALCOHOL COPOLYMER (EVOH)

35 mol% Ethylene Content

## Application

Soarnol™ BG3522B is a 35 mol% ethylene content standard grade of Soarnol™ with a high melt flow rate. Soarnol™ BG3522B is specifically designed for co-extrusion coating applications.

## General Properties

Properties	Unit	Value
Ethylene Content	mol%	35
MFR <sup>1)</sup> (210 degree C, 2160g)	g/10min	22
Volatile Matter	%	< 0.3
Melting Point <sup>2)</sup>	degree C	178
Crystallization Temp. <sup>2)</sup>	degree C	156
Glass Transition Temp. <sup>2)</sup>	degree C	59
Density <sup>3)</sup> (23 degree C)	g/cm <sup>3</sup>	1.18
Oxygen Permeability <sup>4)</sup> (20 degree C x 65%RH)	cc.20µm / m <sup>2</sup> .day.atm cc.mil / 100inch <sup>2</sup> .day.atm	0.5 0.025

1): Measured with Melt Indexer

2): Measured with DSC, both heating and cooling speeds of 10 degree C/min

3): Measured with Micromeritics Gas Pycnometer

4): Measured with OXTRAN 2/20 (MOCON)

\*The above figures are representative values and are not guaranteed.

Melt Viscosity




Fig. 1 Melt Viscosity of Soarnol™ BG3522B

Example of Processing

Extruder : 40 mmφ L/D = 28  
 Screw : full flight, constant pitch type, C.R. = 3.5  
 Screen pack : 90/90 mesh

Processing Temperature

	C <sub>1</sub>	C <sub>2</sub>	C <sub>3</sub>	C <sub>4</sub>	C <sub>5</sub>	AD
deg.C	170-200	185-210	200-230	200-230	200-230	200-230
deg.F	338-392	365-410	392-446	392-446	392-446	392-446

Revised date on Apr. 1st 2020

## Quality and Safety for Application of Soarnol™ BG3522B

High quality Soarnol™ is produced by Okayama plant in Japan, NOLTEX L.L.C. in U.S.A. and NIPPON GOHSEI UK Ltd. in U.K.. All plants are certified to meet the requirement of ISO 9001.

Soarnol™ contains no heavy metals or other harmful substances. Soarnol™ meets the Food Sanitation Standards of various countries.

Please contact us to inquire about food product hygiene for the various Soarnol™ brands or for food hygiene conformity in other countries.

U.S.A : US FDA 21, C.F.R. §177.1360

JAPAN : Ministry of Health and Welfare Announcement No.370(1959) and Its Latest Amendment No.18(1994)

Voluntary Standards for Food Contact Substances and Polymers (JHOSPA)

EU : Commission Regulation (EU)No. 10/2011 and its amendments

CHINA : GB9685, GB4806.6 and their amendments

## Soarnol™ Contacts

Soarus L.L.C.	3930 Ventura Drive, Suite 300, Arlington Heights, IL 60004, USA TEL +1-847-255-1211 FAX +1-847-255-4343
Mitsubishi Chemical Corporation Head Quarters	1-1, Marunouchi 1-Chome, Chiyoda-Ku, Tokyo 100-8251, Japan TEL +81-3-6748-7803 FAX +81-3-3286-1239
NIPPON GOHSEI Europe GmbH	Merowingerplatz 1a, D-40225, Duesseldorf, Germany, Life Science Center TEL +49-211-385488-0 FAX +49-211-385488-29
Mitsubishi Chemical (China) Co.,Ltd.	38-39th Floor, Grand Gateway Office Tower 1, 1 Hongqiao Rd.,Xuhui District, Shanghai, 200030 China TEL +86-21-5407-6161 FAX +86-21-5407-6262
Mitsubishi Chemical Asia Pacific Pte. Ltd.	41 Science park Road #02-12/13 The Gemini Singapore Science Park II Singapore 117610 TEL +65-6263-0970 FAX +65-6423-1562
Processing-Technique Development Center	3-10, Ushiodori, Kurashiki, Okayama 712-8054, Japan TEL +81-86-455-5214 FAX +81-86-455-5289

URL: <http://www.soarnol.com/>

<http://www.soarus.com/>

<https://www.m-chemical.co.jp/>